

How To Use Nanolex Matte Spray Sealant

This product can be stored for up to 24 months (in a dry, temperature stable environment)

Consumption:

Cleaner: appr. 10ml/m² (~70 ml for paint + alloys)

Sealant: appr. 5ml/m² (~40 ml for paint + alloys)

Processing temperature: 5-30°C - Avoid direct sunlight and/or high air humidity.

IMPORTANT: Before you use a Nanolex Car Care product please make sure you wear suitable protection gear – we always recommend to use Latex- or Nitril gloves to make sure your hands are protected from any possible damage to your skin.

- 1.** Nanolex Matte Spray Sealant can be applied directly to all lacquer surfaces. The lacquer surface must be dry and free of contamination or dust. We strongly recommend to use Nanolex EX directly before the application to make sure that all oils/fillers and other dirt are removed completely from the surface.
- 2.** Spread approx. 1 – 2 ml of Nanolex Matte Spray Sealant on an applicator pad (we recommend standard cotton makeup pads) and apply it sparingly by rubbing in with light pressure and permanent circular movements.
Remove excess material after 5-10 minutes with a soft microfiber cloth.
- 3.** Directly after polishing the sealant is dry and the surface can be touched. At normal ambient temperature the sealant is completely cured after approximately 60 minutes.

Please read the separate information on how to clean your car and wheels after a treatment with Nanolex Paint & Alloy Wheel sealants.

If you have any questions regarding our products or in case you need support during the application please feel free to get in touch with our staff any time.

The information on this data sheet is based on the current status of technical development as well as our experience with the product. However, given the variety of surfaces and ambient conditions, the information provided on this data sheet shall in no way diminish the responsibility of the user to ensure with due care, that our product is suited for the intended purpose, surface and application conditions. Since application and processing lie outside our purview, no manufacturer liability shall be derived from the information provided herein. Our General Terms and Conditions of business shall apply in all cases. All information is subject to change without notice.